


COPPER GRAPHITE



**E
9
5
0
C**

Typical Physical Properties

Average Particle Size (μ):	7
Flexural Strength (psi):	12,000
Apparent Density (gm/cc):	2.76
Hardness (Shore) :	65
Electrical Resistivity ($\mu\Omega$ in):	84

Typical E-950C Applications

Thin Ribs

Very Fine Detail

Deep Cavities

Carbide Machining

Alternative to Copper Tungsten